

STOPAQ® OUTERWRAP PVC

Product Information

Generic type: UV-resistant, flexible polyvinyl chloride tape, coated with a modified, pressure sensitive rubber resin adhesive.

Product Description: STOPAQ® Outer Wrap PVC is used for mechanical protection of corrosion protective systems, such as the STOPAQ® Wrappingband CZH and CZ. The Outer Wrap has high puncture and aging resistance. Is well suited for above-ground, under ground and submerged applications. The heavy-duty adhesive layer provides high adhesion strength to the outer surface of the STOPAQ® Wrappingband as well as to its own backing. The Outer Wrap has a good resistance to impacts and abrasion as well as resistance against the influences from alkalis and acids.

Features:

- Easy to apply
- Cold applied
- Good conformability
- Good adhesion to STOPAQ® Wrappingband as well as to its own backing
- Excellent impact resistance
- Wide temperature range for service

Benefits:

- Extremely well suited for hand application
- Easy to stretch and to apply for protection of STOPAQ® corrosion protected irregular shapes, such as valves, flanges, bends and tee's
- Resists impacts and indentations which may occur during installation and backfilling
- Very high resistance to ageing - even when exposed to max or min temperature for longer periods of time

Mechanical Protection examples:

Piping & Vessels: STOPAQ® corrosion protected carbon steel pipelines (underground, above ground, immersed), structures and reservoirs.

Field Joints: STOPAQ® corrosion protected field-weld joints of pipelines, on-shore.

Product Properties_STOPAQ® Outer Wrap PVC

Colour	Black (matt finish)
Thickness	Total: 0,5mm ± 0,055mm (ISO 9001) (Backing: 0,45mm ± 0,045mm)
Temperature Range	Application +10°C - +65°C Service -45°C - +60°C Application temp. Outerwrap: +10°C - +60°C
Adhesive strength	0,5 N/mm (at 23°C) On STOPAQ® Wrappingband and on itself:
Operation temp.	- 45°C - +60°C
Short term max.	Up to 85°C
Tensile strength	> 10 kg/25mm
Elongation	> 200%

Product Properties_STOPAQ® Outer Wrap PVC on STOPAQ® Wrappingband CZH/CZ

Total Thickness	2,8mm - 3,2mm (ISO 9001)
Impact resistance	Tested at 15 J (EN 12068) at -45°C: no holidays (< 5 min.) at +23°C: no holidays (< 5 min.) at +70°C: no holidays (< 120 min.)
Indentation resistance	10N/mm ² (EN 12068) at 23°C, no holidays (< 5 min.) at 70°C, no holidays (< 120 min.)

General Order Information

Product	STOPAQ® Outer Wrap PVC is available in rolls Wide: 50mm (core ID 1 1/2"), 75, 100, and 150mm (core ID 3"), in 10m* or 30m lengths (* 50mm wide only).
Packaging	Coiled on cardboard cores. Packed in cardboard boxes.
Handling	Handle with care, keep the box always upright.
Storage	Indoor, dry and clean. Storage temperature not above 40°C for a long shelf-life.

Application instruction_Preparation		Bringing into service	
Application equipment	Scissors, knife, and measuring tape.	Bringing into service	Backfilling is possible immediately after completion of the coating application. The STOPAQ® coated, Outer Wrap protected areas should not be exposed to loads from supports and lifting equipment
High humidity	STOPAQ® Outer Wrap PVC can be applied in a humid atmosphere that does not reach the dew point.	Backfilling	Backfill with clean sand without sharp stones or hard lumps of soil.
Work area and substrate	The work area and application surface should be dry and clean and protected against negative weather influences.		
Tape conditions	STOPAQ® Outer Wrap PVC should be dry and have a temperature of 10°C to 30°C for the ease of handling and shaping.		
Application instruction_Short cut			
Wrapping	<p>The STOPAQ® Outer Wrap PVC must be applied with little TENSION.</p> <p>Start the wrapping 3mm with one full circumferential wrap. Leave 3mm of STOPAQ® CZH visible. Then follow with spiral wrapping with minimum 50% overlap. Avoid air-enclosures.</p> <p>End full-circle overlap, Outer Wrap on Outer Wrap: minimum 300mm.</p> <p>Finish the wrapping 3mm inside the STOPAQ® Wrappingband with two straight, TENSIONLESS circumferential wrappings. Cut the tape end in a 45° angle at the downwards side with the longest tip pointing in the direction of the wrapped part.</p>		
Application instruction_Quality Control		STOPAQ® Information	
Visual inspection	The applied Outer Wrap must look smooth and tight and should be shaped around all details and into corners.	Documentation	Extensive information is available on our web-site. Detailed application instructions, "STOPAQ® Technical Standard" can be acquired from our head office and/or local distributor; info@stopaq.com
		Certified staff	The application of STOPAQ® coating systems should always be carried out by certified personnel



STOPAQ® Europe B.V.

Gasselterstraat 20
9503 JB Stadskanaal
[T] +31 (0)599 696170
[F] +31 (0)599 696177
www.stopaq.com

DISCLAIMER: To the best of our knowledge, the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Stopaq Europe B.V. to verify correctness before specifying and ordering. No guarantee of accuracy is given or implied. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is replacement of products. No other warranty or guarantee of any kind is made by Stopaq Europe, express or implied, statutory, by operation of law, or otherwise, including merchantability and fitness' for a particular purpose. Stopaq® is a registered trademark of Stopaq Europe B.V.